




Brazil

	Table of contents Matéria (Rio de Janeiro) ▾	 ▾
Text (EN) ▾	 PDF ▾	

Articles • Matéria (Rio J.) 28 (2) • 2023 •

<https://doi.org/10.1590/1517-7076-RMAT-2023-0112> COPY

Evaluation of properties of fibre reinforced asphalt mix with copper slag as the filler

ABSTRACT

Rapid economic growth of countries requires continued expansion of the road network, which requires a huge volume of natural resources. Broken stones of coarse and finer sizes cause depletion of natural resources. On the Other hand, disposal of industrial waste is a great challenge. Hence, this research, the conventional filler (quarry dust) completely replaced by copper slag and glass fibre included in the asphalt mix varying from 0.1% to 0.4% by volume of asphalt mix with na incremente of 0.1%. The volumetric and mechanical properties investigated in the laboratory. The experimete results concluded that the asphalt mix with copper slag as filler and the fiber length of 8 mm with 0.2% by volume of mix exhibited optimum performance without compromising the volumetric properties.

Keywords

Fibre; Copper Slag; Fatigue; asphalt mix; Indirect tensile strength (ITS).

1. INTRODUCTION

In India, 90% of the roads are constructed with flexible pavement, and the total road network covers a total length of 54.83 lakh kilometers [¹]. The incorporation of wastes such as roofing shingle wastes, glass, flyash, municipal solid waste combustion ash, rubber tires, carpet fiber, by-products of coal ash, blast furnace slag, and steel slag, and recycled plastic are available in huge quantities from industry for Highway construction, reducing the use of conventional natural resources and disposing of constraints [²]. Industrial waste was easy to incorporate in pavement construction to maintain good quality [³]. The construction and lifecycle costs were found to be less When compared to the conventional asphalt mixes used in road construction [⁴]. The Indian Road Congress (IRC) has given guidelines for the use of waste materials such as blast furnace slag, steel slag, and copper slag for incorporation in different pavement layers both in flexible and rigid pavement construction constructed in rural areas [⁵]. Copper slag is one of the huge industrial wastes produced by the copper industry. In the global market, Chile ranked number one in copper

This site uses cookies to ensure you get a better browsing experience. [Read our Privacy Policy.](#)

production with a share of 30% of total global copper production, with 80% of the economic activity depending on the generation of copper raw material [6]. Nearly 2.2 to 3.0 tons of copper slag are generated for every one-tone production of copper, leading to the generation of 4.5 million tons of copper slag very year; as of now, a total of 50 million tons of copper slag have been accumulated [7 , 8]. Every year, nearly 6,000 metric tons (MT) of copper slag are produced in Tamil Nadu, India, by Sterlite Industries. As a result, there searchers believe that the only scientific solution to safe disposal is to reuse the quantity of copper slag that is accumulated in the land fill [6 , 9]. In chemical analysis, it was found that the copper slag has the following chemical composition: iron oxide: 30 to 40%, silicon oxide: 35 to 40%, aluminum oxide: 0 to 10%, and calcium oxide: 0 to 10% [6 , 10]. The copper slag was categorized as non-hazardous material [11 , 12 , 13]. The asphalt mixes having 60% reclaimed asphalt pavement with 15% copper slag and 70% reclaimed asphalt pavement with 7.5% copper slag showed better performance without compromising on the following properties: resistance to rutting, fatigue life, dynamics tiffness, and moisture resistance [14]. The copper slag-contained asphalt mix has a high resistance to moisture and medium-to-long-term ageing [15]. The indirect tensile strength and resiliente modulus get increased for different temperatures (25 °C, 35 °C, 45 °C, 55 °C, and 60 °C) for the copper slag-contained asphalt mix when compared to the conventional asphalt mix [16]. From SEM analysis, it was found that there was no difference between the copper slag-incorporated asphalt mix and conventional asphalt mix [17]. Researchers changed the bitumen with polymers like chemical modifiers, crumb rubber, and natural rubber latex to improve the mix's fatigue life, aging, resistance to rutting, and resistance to water [18]. The use of fibers started in the 1950s. In the bituminous overlay, they used wiremesh as reinforcement to arrest the reflective cracking [19]. The use of fibers improves the strain energy absorbed when the asphalt mix is subjected to fatigue and fracture [20]. It was observed that there was improvement in the tensile strength of the asphalt mix with the inclusion of fibers [21]. The bituminous concrete incorporated with synthetic fibers has been investigated throughout the world by researchers to improve the mechanical Properties of the asphalt mix [22 , 23].

The asphalt mix with 0.25% glass fiber content performed better without compromising the standard permissible values for the mechanical and volumetric properties of asphalt mix. The indirect tensile strength increased by 5% when compared to the conventional asphalt mix. The rutting resistance increased by 20% when compared to the conventional mix [24]. The fiber-contained asphalt mix had high resistance to high and low temperatures, and at the same time, it had high resistance to moisture sensitivity [25]. In the fiber-contained asphalt mix at a low temperature of -20 °C, it was found that there was an 80% increase in post-crack toughness in the mix [26]. Short fiber reduces the stress to the maximum extent, improving the viscoelastic and effective modulus of a fiber-contained asphalt mix [27]. The aramid-polyalphaolefin fibers in the asphalt mix with a dosage of 0.45 kg/m³ showed na increase in dynamic modulus [28].

Performance of an aramid-polyalphaolefin fiber-reinforced bituminous mix under the very low temperature of -20 °C in the laboratory. By performing rectangular and semi-circular bending tests with conventional bitumen of 50/70 grade and polymer-modified bitumen. Both the bitumen-containing asphalt mixes showed positive effects with the inclusion of fiber [29]. High fracture energy was observed in the asphalt mix with fiber when compared with the conventional asphalt mix; the same trend was noted on the stress factor also. On the other hand, the low reduced frequency observed on the dynamic modulus test for all three types of the mix, such as

This site uses cookies to ensure you get a better browsing experience. [Read our Privacy Policy.](#)

conventional asphalt mix, asphalt mix with fiber, and asphalt mix with the modified binder. The properties such as toughness and tensile strength get improved, which implies that the asphalt mix containing polyester fiber has high durability against fatigue loading [30]. The inclusion of

polypropylene fiber in dense graded asphalt mix improved properties such as resistance to moisture sensitivity, resilient and dynamic modulus, flow number, fatigue resistance, and fracture energy [31].

In the literature review, it was found that the industrial waste copper slag obtained from the copper industry has improved mechanical Properties such as fatigue life, indirect tensile strength, resistance to moisture sensitivity, rutting resistance, increased energy absorption capacity, and increased stiffness, all without compromising the volumetric properties required in the asphalt mix. Thus, the copper slag maybe substituting for the conventional natural aggregate utilized in bituminous mixes. The mechanical properties of bituminous mix improved with the addition of fibers such as steel fiber, synthetic fibers such as glass fiber, polypropylene fiber, carbon fiber, etc. The fiber acts as the bridge on the failure plane while underload. The following characteristics, such as post-cracking behavior, fatigue life, dynamic modulus, resilient modulus, rutting, Marshall stability, flow, toughness, tensile strength, energy absorption, etc., get improved without compromising there quired volumetric properties in the asphalt mix with fiber than in the conventional mix without fiber. Simultaneously, the life cycle cost decreased due to improved performance and lower maintenance costs. There were no research studies found out with the combination of fiber sand partial replacement of copper slag bituminous mixes. Hence, research on the addition of polypropylene fiber combined with copper slag in bituminous concrete mixes was proposed in this paper.

2. MATERIALS AND METHODS

2.1. Bitumen

When heated, the thermo-viscous substance known as bitumen transforms into a liquid state. This study made use of bitumen with a viscosity grade of 30, also known as VG 30, approved for usage on Indian roads [1]. The properties of bitumen used in this research are shown in Table 1.

2.2. Aggregate (broken stones)

Marshall specimens are prepared using shattered stones of average sizes (12 mm and 6 mm) from a quarry available nearby. In order to prepare a quality asphalt mix, the shattered stones are screened to eliminate harmful impurities that affect the efficiency of the asphalt blend. The physical properties of the shattered stones used in this research are shown in Table 2.

2.3. Copper slag (as partial replacement of dust)

Copper slag acquired for this study from Sterlite Industries, a copper-producing company based in the state of Tamil Nadu in India. Both of the slag's physical attributes are broken down in depth in Table 3. Figure 1(a) show the copper slag used in research.

2.4. Fibre

The incorporation of fibres into bituminous mix boosts engineering parameters such as stiffness fatigue life and rutting (permanent deformation along the wheel path) and therefore, fiber-based bituminous mix has emerged as a feasible choice for the building of asphalt pavements.

This Figure 1(b) shows the glass fibre used in this research. The experimental results of the Glassy Policy. tabulated in Table 4.

OK

2.5. Aggregate combined gradation

Brazil
 The raw aggregate and copper slag collected from source not suitable for the preparation of asphalt mix (semi dense bituminous mix, grading 2 type (according to MoRTH [1])). In order to overcome this issue, it proposed in this research to segregate the aggregate and copper slag obtained from the source based on the size of the particles. The aggregates were grouped into particle sizes passing through sieve sizes such as 12.5 mm, 6 mm, 4.75 mm (quarry dust), and copper slag (size less than 4.75 mm). The segregated aggregates mixed at certain proportions to obtain aggregate particles that would be suitable for the preparation of asphalt mix.

For conventional combined aggregate gradation, aggregate sizes of 12.5 mm were retained at 10%, 6 mm at 30% and quarry dust (size less than 4.75 mm) at 60% (by weight) retention on a specific sieve size were cumulated to prepare aggregate to satisfy the MoRTH (Ministry of Road Transport and Highways). The aggregate specification (semi dense bituminous mix, grading 2 type) for the preparation of the Marshall specimen shown in Figure 2. Similarly, for combined aggregate gradation with copper slag as filler. The aggregate size of 12.5 mm by 10%, 6mm by 30%, and copper slag (size less than 4.75 mm) by 60% (by weight), retained at a specific size, was utilized to produce the required graded aggregate, which satisfies the MoRTH (Ministry of Road Transport and Highways) [1] specification for the preparation of Marshall specimens, as shown in Figure 3.

2.6. Phase diagram of asphalt mix

Figure 4 depicts the schematic diagram of the asphalt mixture. When bitumen coated to the aggregate piece, aggregate used in asphalt mix absorbs part of the asphalt. The remaining bitumen forms a coating on the surface of the aggregate used in the asphalt mix. Air pockets occur within the asphalt mix, which is why the aggregate particles do not combine with the asphalt to create a solid mass. As illustrated in Figure 5, the four main constituents of hot mix asphalt are crushed aggregate, bitumen absorbed by the crushed aggregate, air, and bitumen that has not ingested into the crushed aggregate (useful bitumen).

2.7. Asphalt mix references

The design parameters selected by MoRTH (Ministry of Road Transport and Highways) for the formulation of the mixtures are listed in Table 5. Different combinations of fiber lengths and doses used to prepare bituminous mixes for the control mix and the mix with partial substitution of conventional aggregate by copper slag. Seventeen mix designs listed in Table 6 done in laboratory. The mixtures labeled as MC (A-B), where M stands for mix, C represents the proportion of conventional aggregate replaced by copper slag, A represents the fiber length in millimeters, and B represents the fiber dosage by weight of aggregates. For instance, MC (0-0) represents the control mix with zero percent copper slag replacement, zero fiber length, and zero fiber dose. M60 (4-0.10) denotes 60% substitution of conventional aggregate with copper slag in a fiber-added bituminous mix with 4 mm of fiber length and 0.10% fiber dosage. The Marshall mix design procedure for control mix, the partial substitution of copper slag with conventional aggregate, and the glass fiber added asphalt blends with all feasible combinations of fiber dosages (0.1%, 0.2%, 0.3%, and 0.4% by weight of mix) and fiber lengths (4 mm, 8 mm, 12 mm, and 16 mm).

This site uses cookies to ensure you get a better browsing experience. Read our [Privacy Policy](#).

OK





3. PERFORMANCE OF ASPHALT MIX WITH INCLUSION OF FIBRE AND COPPER SLAG AS FILLER

3.1. Volumetric properties




Matéria (Rio de Janeiro) ▾

In the final phase of asphalt mix densification, there must be air pockets in the asphalt mixture. Nevertheless, the mixture would become flimsy because of excessive air pockets due to Young's modulus and fatigue life factors. The much more challenging and time-consuming process in the design mix process is evaluating and choosing the aggregate proportioning to achieve the desired thresholds for VMA (voids in mineral aggregate) and VFB (voids filled with bitumen). In order to obtain a long-lasting bitumen coating thickness, a minimal level of VMA must be applied. A thin coating of asphalt on the asphalt mixture leads to low durability, which results from raising the density of the broken stones until they fall below the lowest VMA values procured.

The quantity of air void spaces in the bituminous mix affects how long the asphalt pavement will survive. This is because the air holes in the bituminous mixture are much smaller, making it much less porous. When there are too many air holes, corrosive air and water can get into the mixture. On the other hand, a low concentration of air-voids can cause blockage, which is when extra bitumen leaks through the asphalt mix and lands on the pavement surface. Air content and density are intimately associated. The proportion of void spaces inside the asphalt mix decreases as density increases, and vice versa.

According to Section 500 in MoRTH for SDBC (semi-dense bituminous mix), the recommended lowest air voids are 3 percent and the highest air voids are 5 percent to achieve a quality asphalt mix for better performance. From  Figures 6 and , it can be observed that for the fibre lengths of 4 mm and 8 mm up to 0.2% fiber by weight of mix, the air voids (V_a) and voids in mineral aggregate (VMA) fall within the limits according to the MoRTH [1] specification shown in  Table 5. As the dosage increases beyond 0.2% by weight of mix, the air voids (V_a) and voids in mineral aggregate (VMA) value falls above the upper recommended limits. Similarly, in the case of 12 mm and 16 mm length fiber, up to 0.1% dosage, the V_a and VMA fall within the recommended limits, and beyond 0.1% dosage, the V_a and VMA values fall above the recommended value given in  Table 5.

The voids filled with bitumen measure how much bitumen used to fill flaws inside the densified aggregate mass. It and the bitumen-void proportion are interchangeable terms. The voids filled with bitumen are crucial since bitumen serves as a good indicator of overall longevity and exhibits a strong relationship with percentage density. Insufficient bitumen prevents longevity as well as causes this to be too dense under vehicle movement and bleed unless the VFA is too minimal. The primary objective of the voids filled with bitumen is to prevent a less long-lasting hot mix asphalt mixture from forming from a thin bitumen coating on the broken stone particles in low-traffic environments.

 Figure 8 shows that for fibre lengths of 4 mm and 8 mm up to 0.3% fibre dosage by weight of mix, voids filled with bitumen (VFB) fall within the MoRTH specification shown in  Table 5. As the dosage increases beyond the 0.3% dosage by weight of mix, the voids filled with bitumen (VFB) value falls above the upper recommended limits. Similarly, in the case of 12 mm and 16 mm length fiber, up to 0.2% dosage of fiber, voids filled with bitumen fall within the recommended limits, and beyond 0.2% dosage of fiber, VFB values fall above the recommended value given in  Table 5.

This site uses cookies to ensure you get a better browsing experience. Read our [Privacy Policy](#).

3.2. Mechanical properties

The prepared Marshall specimen was tested using standard ASTM D 1559 [33], which is described as the peak load borne by the Marshall specimen at a normal test temperature of 60 degrees centigrade. Flow value refers to the specimen's relationship to plastic flow during a Marshall Specimen rupture.

With an increased dose of glass fiber, stability values for all fiber lengths decreased. It was caused by the presence of additional fibers in the mixture, which may also cause sliding between broken stones and lower stability values. The interaction sites between the broken stones used in the asphalt mix decrease with an increased dose of glass fiber, which lowers the stability values [34]. The stability value observed was much higher than the 8.2 kN baseline criteria set by MoRTH for SDBC asphalt mixes throughout all variations, as shown in Figure 9. The least stability observed was 15.7 kN for a mix with 16 mm fiber length at a dosage of 0.40%. The highest stability observed was 22.45 kN for an 8-mm fiber length at a dosage of 0.1%. Higher the stability, higher resistant to fatigue cracking because they are less likely to deform under load [35]. The performance of asphalt mix decreases with increase in dosage of fibre due to reduced workability which make the asphalt mix more stiff and difficult to work with [36].

According to Section 500 of the MoRTH for SDBC (semi-dense bituminous mix), the recommended lowest flow value is 2 mm and the highest flow value is 4 mm to achieve a quality asphalt mix for better performance. From Figure 10, for fiber dosages of 0.1%, 0.2%, and 0.3% of 4 mm fiber length, the flow value falls within the recommended lower and upper limit values, while for 0.4% of 4 mm, the flow value exceeds the recommended upper limit. For a fiber dosage of 0.1% and 0.2% of 8 mm fiber length, the flow value falls within the recommended lower and upper limit values, and for a dosage of 0.3 and 0.4% of 8 mm, the flow value exceeds the recommended upper limit. For a fiber dosage of 0.1% of 12 mm fiber length, the flow value falls within the recommended lower and upper limit values, and for a 0.2%, 0.3%, and 0.4% dosage of 12 mm, the flow value exceeds the recommended upper limit. For a fiber dosage of 0.1% of 16 mm fiber length, the flow value falls within the recommended lower and upper limit values, and for a 0.2%, 0.3%, and 0.4% dosage of 16 mm, the flow value exceeds the recommended upper limit. The flow value increases with increase in fibre dosage at lower dosage, beyond that, the flow value decreased due to poor workability of the mix (Meherz et al 2005). At the lower dosage of glass fibre volumetric parametres are within the required limit and improved the mechanical properties such as stability, fatigue, indirect tensile strength are improved to greater extend [37].

Overall ideal bitumen content (OBC) of a control mix (i.e., without fiber) is 5.52%, while the OBC percent for the glass fiber-modified bituminous mix was 5.41%, 5.52%, 5.65%, and 5.71 for doses of 0.1%, 0.2%, 0.3%, and 0.4%, respectively. Various fiber lengths have indeed produced OAC findings (8 mm, 12 mm, and 16 mm). For different lengths and dosages, OAC varied from 5.43% to 5.84%. The OAC was 5.5% by weight of asphalt mixture at a dosage of 0.2% and 8 mm-length glass fiber, which already have greater stability and fulfill all those other required qualities, taking into consideration the strength and volumetric characteristics of all glass fiber lengths and dosages.

4. INDIRECT TENSILE RIGIDITY MODULUS (ITRM)

This site uses cookies to ensure you get a better browsing experience. Read our [Privacy Policy](#). The indirect tensile rigidity modulus (ITRM) test in accordance with the protocol outlined in BS EN 12697-26 [38], "Hot mix asphalt mixes - Evaluation procedures of hot mixture asphalt - Part 26: Rigidity," that complies with the British standard. Through administering half-sinusoidal stress on

the Universal Testing Machine (UTM HYD 25) with such targeted pulse duration, targeted transverse displacement, and a targeted warmth, the cylindrical specimens were subjected to indirect tensile strain for such an investigation. To determine the impact of glass fibers on the rigidity modulus of asphalt mixtures, experiments were carried out on each of the 17 blends, as shown in Table 6, to evaluate glass fibers' impact on asphalt mixtures' rigidity modulus. The typical of loading format is shown in Figure 11 and rigidity modulus test setup is shown in Figure 12.

The estimated rigidity modulus for every load cycle was calculated using observations from the five load cycles by using equation 1 below.

$$S_m = \frac{F \times (v + 0.27)}{z \times h}$$

(1)

Where,

S_m = rigidity modulus in Mpa

F = maximum of compressive force imposed (N)

v = poisson ratio

z = the magnitude of the lateral displacement observed throughout the compression cycle (mm)

h = testing samples average girth

Furthermore, it was assumed that all specimens would have a Poisson's ratio of 0.35. Through the use of the given equations, the observed rigidity modulus was converted to a load area ratio of 0.60 by equation 2, given below.

$$S'_m = S_m \times (1 - 0.332 \times (\log(S_m) - 1.82) \times (0.60 - k))$$

(2)

Where,

S'_m – adjusted rigidity modulus to that 0.60 load area value (Mpa)

S_m – at a load factor of k , the measured rigidity modulus (Mpa) @ °C.

k – Assessed load area ratio

The sample taken outside of the testing apparatus, turned 90 degrees around its lateral axis, and its rigidity modulus measured. They replicated the computation and testing. The rigidity modulus of the sample was determined to be the average value of two specimens. The rigidity modulus findings for the control sample and the bitumen mixes with fiber incorporated are shown in Figure 13 and the findings are explained below.

This site uses cookies to ensure you get a better browsing experience. Read our [Privacy Policy](#).

OK

Overall, all fiber length stiffness moduli dropped when the amount of glass fiber increased. Due to the incorporation of glass fibers, the blend appeared to have poorer compressive values, which decreased the rigidity modulus. This enabled the blends to slide between broken stones [37]. The rigidity modulus declined with an increase in fiber dosage, typically with all conceivable configurations of fiber dosages (0.1%, 0.2%, 0.3%, and 0.4% by mass of blend) and fiber lengths (4 mm, 8 mm, 12 mm, and 16 mm). Increased fiber dose lowers the mix's compressive strength, which in turn lowers the stiffness modulus [34]. With the concentration of 0.10% of glass fiber, the rigidity modulus reached its maximum for 4 mm (2037 MPa), 8 mm (2211 MPa), 12 mm (2319 MPa), and 16 mm (2143 MPa), which have been, correspondingly, around 16.17%, 9.01%, 4.57%, and 11.81% lower stiff than the reference samples. At a dose of 0.1% by mass of shattered stones, the rigidity modulus with the maximum value reported to be 2319 MPa for 12 mm fiber length.

5. FATIGUE TEST

This research used the technique outlined according to BS EN 12697-24 [39], "Asphalt mixes - Testing procedure for asphalt hot mix - Part 24: Resistant to Fatigue," to perform fatigue endurance experiments on compacted asphalt specimens.

Throughout this experiment, the Universal Testing Machine (UTM) applied sinusoidal stress to cylindrical samples. Figure 14 depicts the indirect tensile fatigue test setup that employed in this research. The overall number of loads applied that resulted in full breakage of the sample used to calculate the fatigue performance, as shown in Figure 15. The correlation between the total lateral deformation and the logarithmic number of loading conditions revealed the fracture life.

Figure 15 shows the results of the fatigue tests (periodic load, indirect tensile) that were done in the lab. The reference asphalt mixture's fatigue life lasted 9452 cycles. With fiber doses up to 0.2%, the inclusion of glass fiber substantially enhanced the asphalt blend's fatigue performance. The fatigue performance revealed that there were decreases for all fiber lengths and an increment in fiber concentration of up to 0.2%. According to JAHROMI and KHODAII [40], its longer fatigue performance may have resulted from the fibers' homogeneous distribution throughout the asphalt mixture, resistance to shearing displacement, and suppression of shattered stone movement at lower dosages. Consequently, by postponing fracture onset and propagation and gaining high fracture toughness, the similarity noted in glass fiber contained an asphalt mixture. The fatigue resistance at the dosage of 0.2% with 4 mm (10960 cycles), 8 mm (13450 repetitions), 12 mm (12020 repetitions), and 16 mm (12418 repetitions), which had been approximately 15.98%, 42.33%, 27.20%, and 31.40% greater fatigue life than the conventional asphalt blend, resulted in the maximum fatigue resistance. The optimum fatigue resistance for 8 mm fiber length was observed at a concentration of 0.2% (13450 cycles), which was 42.33% more than the reference asphalt mix. The blend containing 8 mm of fiber length at a concentration of 0.2% showed the longest fatigue resistance. The relation between fatigue cycle and stability of asphalt mix is a complex one that is influenced by the factors such as the type and amount of asphalt binder, the aggregate gradation, the air void content, and the temperature. In general, however, it can be said that the higher the fatigue cycle are observed with inclusion of fibre, which make the mix high stable, the fibre contained asphalt mix can withstand more repeated loading before it fails (RAMESH *et al.* [41]).

This site uses cookies to ensure you get a better browsing experience. Read our [Privacy Policy](#).

6. INDIRECT TENSILE STRENGTH

OK

The indirect Tensile strength was done accordance with the D6927 [42] and D3549 [43].

According to D6927 [42] -compliant loading machine must be able to deliver a vertical load with a regulated displacement rate while simultaneously monitoring the force and displacement in order to undertake the investigation. Slightly curved iron loading sheets with a tested sample's normal circumference as its curvature radius. The length of the loading strands must be longer than the sample width, and the loading strands' outside ends must be mildly beveled to eliminate jagged corners. The heating system must be sufficient to keep the samples below 61 °C, the experiment temperature. The bituminous sample should have a minimum diameter of 101.6 mm and at least 50.8 mm thickness. According to D3549 [43], thickness of the bitumen specimen must be correct to within 1 mm. The specimen was kept at 61 °C during testing by immersing the specimen in the water for a minimum of thirty minutes and a maximum of 120 minutes, as indicated in

Figure 16(a). Once out of the water bath, set the specimen on the lowest loading plate. Lower the top loading pad into minor contact with the sample by gradually lowering it as shown in

Figure 16(b). Ensure that the loading bars are parallel and centered. The time between the withdrawal of test specimens from the bath and the final load should not be greater than 2 minutes. Once the ultimate load is attained, apply a vertical ramp force. The suggested rate of displacement is 50 ± 5 mm/min.

Figure 17 illustrate the outcomes of indirect tensile strength at 60 °C done in the lab. With fiber doses up to 0.2%, the inclusion of glass fiber substantially enhanced the indirect tensile strength. The indirect tensile strength at the dosage of 0.2% with 4 mm (114 kpa), 8 mm (126 kpa), 12 mm (119 kpa), and 16 mm (112 kpa), which had been approximately 23.91%, 36.96%, 29.35%, and 21.74% greater indirect tensile strength than the conventional asphalt blend, resulted in the maximum indirect tensile strength. The optimum indirect tensile strength for 8 mm fiber length was observed at a concentration of 0.2% (126 kpa), which was 36.96% more than the reference asphalt mix. The blend containing 8 mm of fiber length at a concentration of 0.2% showed the longest ITS resistance. The increase in ITS with inclusion of fibre, which bridge the gaps between the aggregate particles, which increases the tensile strength of the asphalt mix. Fibers help to distribute the load more evenly throughout the asphalt mix, which reduces the localized stresses that can lead to cracking MAHERZ and KARIM [44], fibers are tough and ductile, which can withstand high tensile stresses without breaking [45]. Overall, fibers are an effective way to improve the indirect tensile strength of asphalt mix. They are strong, ductile, and corrosion-resistant, which makes them well-suited for use in pavements that are subjected to heavy traffic and harsh environmental conditions

7. CONCLUSIONS

From the laboratory investigation of the bituminous mix with 100% copper slag as filler and glass fiber dosages of 0.1%, 0.2%, 0.3%, and 0.4% by weight of the mix, the following conclusions are drawn:

- The stability of bituminous mixes decreases gradually for dosages of 0.1%, 0.2%, 0.3%, and 0.4% with glass and copper slag as filler, but the obtained stability values are greater than the minimum requirement recommended by the MoRTH specification for all the dosages of fiber.

This site uses cookies to ensure you get a better browsing experience. Read our [Privacy Policy](#).

- The fatigue strength of bituminous mixes are increased with glass fiber up to 0.2% with copper slag as filler, beyond that the fatigue life get decreased.

- The indirect tensile strength of bituminous mixes increased with glass fiber up to 0.2% with copper slag as filler, beyond that the fatigue life get decreased.
- Brazil
- The stiffness modulus of the bituminous mix decreased with glass fiber and copper slag as filler.
- Matéria (Rio de Janeiro) ▾
- Overall, the optimum performance of the asphalt mixture found at 8 mm glass fibre with dosage of 0.2%.

8. BIBLIOGRAPHY

- [1] MORTH: MINISTRY OF ROAD TRANSPORT & HIGHWAYS, *Specifications for Road and Bridge Works (Fifth Revision)*, New Delhi, Government of India, 2013.
- [2] Schroeder, R.L., "The use of recycled materials in highway construction", *Road and Transport Research*, v. 3, pp. 12–27, Feb. 1994.
- [3] Lawson, A., ELLIOTT, R.C., ROWE, G.M., *et al*, "Assessment of suitability of some Industrial By-products for use in Pavement Bases in the United Kingdom", *Transportation Research Board*, n. 1486, pp. 114–123, 1995.
- [4] Sybilski, D., Mirski, K., Kraszewski, C., "Use of industrial waste materials in road construction in Poland", In: *International RILEM Conference on the Use of Recycled Materials in buildings and structures*, Barcelona, Spain, pp. 351–360, 2004.
- [5] INDIAN ROAD CONGRESS, "IRC SP 121-2018: guidelines for use of iron, steel and copper slag in construction of rural roads", In: *Indian Road Congress*, pp. 1–34, 2018.
- [6] Atienza, M., Lufin, M., Soto, J., "Mining linkages in the Chilean copper supply network and regional economic development", *Resources, Conservation and Recycling*, vol. 43, pp. 353–360, Mar. 2018.
- [7] Gorai, B., Jana, R.K., Premchand., "Characteristics and utilization of copper slag—a review", *Resources, Conservation and Recycling*, v. 39, n. 4, pp. 299–313, Nov. 2003. doi: [http://dx.doi.org/10.1016/S0921-3449\(02\)00171-4](http://dx.doi.org/10.1016/S0921-3449(02)00171-4)
» [https://doi.org/10.1016/S0921-3449\(02\)00171-4](https://doi.org/10.1016/S0921-3449(02)00171-4)
- [8] NAZER, A., PAYÁ, J., BORRACHERO, M.V., *et al*, "Use of ancient copper slags in Portland cement and alkali activated cement matrices", *Journal of Environmental Management*, v. 167, pp. 115–123, Feb. 2016. doi: <http://dx.doi.org/10.1016/j.jenvman.2015.11.024>. PubMed PMID: 26615227.
» <https://doi.org/10.1016/j.jenvman.2015.11.024>
- [9] Chen, J.-C., Wei, S.-H., "Engineering properties and performance of asphalt mixtures incorporating steel slag", *Construction & Building Materials*, v. 128, pp. 148–153, Dec. 2016. doi: <https://doi.org/10.1016/j.conbuildmat.2016.10.027>
» <https://doi.org/10.1016/j.conbuildmat.2016.10.027>

This site uses cookies to ensure you get a better browsing experience. Read our [Privacy Policy](#).

OK

[10] Lemougna, P.N., YLINIEMI, J., ADESANYA, E., *et al*, “Reuse of copper slag in high-strength building ceramics containing spodumene tailings as fluxing agent”, *Minerals Engineering*, v. 155, pp. 106448, Aug. 2020.

[11] Alter, H., “The composition and environmental hazard of copper slags in the context of the Basel Convention”, *Resources, Conservation and Recycling*, v. 43, n. 4, pp. 353–362, Mar. 2005. doi: <http://dx.doi.org/10.1016/j.resconrec.2004.05.005>
» <https://doi.org/10.1016/j.resconrec.2004.05.005>

[12] Lori, A.R., Hassani, A., Sedghi, R., “Investigating the mechanical and hydraulic characteristics of pervious concrete containing copper slag as coarse aggregate”, *Construction & Building Materials*, v. 197, pp. 130–142, Feb. 2019. doi: <http://dx.doi.org/10.1016/j.conbuildmat.2018.11.230>
» <https://doi.org/10.1016/j.conbuildmat.2018.11.230>

[13] Modarres, A., Bengar, P.A., “Investigating the indirect tensile stiffness, toughness and fatigue life of hot mix asphalt containing copper slag powder”, *The International Journal of Pavement Engineering*, v. 20, n. 8, pp. 977–985, Aug. 2019. doi: <http://dx.doi.org/10.1080/10298436.2017.1373390>
» <https://doi.org/10.1080/10298436.2017.1373390>

[14] Sharma, R., Khan, R.A., “Durability assessment of self compacting concrete incorporating copper slag as fine aggregates”, *Construction & Building Materials*, v. 155, pp. 617–629, Nov. 2017. doi: <http://dx.doi.org/10.1016/j.conbuildmat.2017.08.074>
» <https://doi.org/10.1016/j.conbuildmat.2017.08.074>

[15] Raposeiras, A.C., Vargas-Cerón, A., Movilla-Quesada, D., *et al*, “Effect of copper slag addition on mechanical behavior of asphalt mixes containing reclaimed asphalt pavement”, *Construction & Building Materials*, v. 119, pp. 268–276, Aug. 2016. doi: <http://dx.doi.org/10.1016/j.conbuildmat.2016.05.081>
» <https://doi.org/10.1016/j.conbuildmat.2016.05.081>

[16] Reddy, M M., SONY, B., GOUD, U.P., *et al*, “Strength rate analysis of hot asphalt mixes of bituminous class-II by part of substituent by conventional concrete with copper slag”, *International Journal of Scientific & Technology Research*, v. 8, n. 12, pp. 1415–1420, 2019.

[17] Jayashree, B., Santhanu, S., Kalaiarasan, B., “Utilization of copper slag in bituminous mix”, *International Journal of Chemical Sciences*, v. 14, n. S1, pp. 188–202, 2016.

[18] Airey, G.D., “Fundamental binder and practical mixture evaluation of polymer modified bituminous materials”, *The International Journal of Pavement Engineering*, v. 5, n. 3, pp. 137–151, Jan. 2004. doi: <http://dx.doi.org/10.1080/10298430412331314146>
» <https://doi.org/10.1080/10298430412331314146>

[19] Zube, E., “Wire mesh reinforcement in bituminous resurfacing”, *Highway Research Record Bulletin*, v. 131, pp. 1–18, 1956.

This site uses cookies to ensure you get a better browsing experience. Read our [Privacy Policy](#).

[20] Brown, S.F., ROWLETT, R.D., BOUCHER, J.L., “Asphalt modification”, In: *Proceedings of the conference on the United States Strategic Highway Research Program: Sharing the benefits*, Thomas Telford, pp. 181–203, 1990.

[21] Busching, H.W., ELLIOT, E.H., REYNEVELD, N.G., "A state of the art survey of reinforced asphalt paving", *Association of Asphalt Paving Technologists*, v. 39, pp. 766–797, 1970.

[22] Wu, S., Ye, Q., Li, N., *et al*, "Effect of fiber (Biochar) on dynamic properties of asphalt mixtures", *Journal of Wuhan University of Technology*, v. 22, pp. 733–436, 2007. doi: <https://doi.org/10.1007/s11595-006-4733-3>
» <https://doi.org/10.1007/s11595-006-4733-3>

[23] TAPKIN, S., ÖZCAN, Ş., "Determination of the optimal polypropylene fiber addition to the dense bitumi-nous mixtures by the aid of mechanical and optical means", *Baltic Journal of Road and Bridge Engineering*, v. 7, n. 1, pp. 22–29, 2012. doi: <http://dx.doi.org/10.3846/bjrbe.2012.03>
» <https://doi.org/10.3846/bjrbe.2012.03>

[24] Eisa, M.S., Basiouny, M.E., Daloob, M.I., "Effect of adding glass fiber on the properties of asphalt mix", *International Journal of Pavement Research and Technology*, v. 14, n. 4, pp. 403–409, Jul. 2021. doi: <http://dx.doi.org/10.1007/s42947-020-0072-6>
» <https://doi.org/10.1007/s42947-020-0072-6>

[25] GUO, F., LI, R., LU, S., *et al*, "Evaluation of the effect of fiber type, length, and content on asphalt properties and asphalt mixture performance", *Materials (Basel)*, v. 13, n. 7, pp. 1556, Apr. 2020.

[26] PERCA CALLOMAMANI, L.A., HASHEMIAN, L., SHA, K., "Laboratory investigation of the performance evaluation of fiber-modified asphalt mixes in cold regions," *Transportation Research Record*, v. 2674, n. 7, pp. 323-335, 2020. doi: <http://dx.doi.org/10.1177/0361198120922213>
» <https://doi.org/10.1177/0361198120922213>

[27] EL-BADAWY, S.M., GABR, A.R., ABD EL-HAKIM, R.T., "Recycled materials and by-products for pavement construction", In: Martínez, L., Kharissova, O., Kharisov, B. (eds), *Handbook of Ecomaterials*, Cham, Springer, pp. 2177–2198, 2019.

[28] KALOUSH, K.E., BILIGIRI, K.P., ZEIADA, W.A., *et al*, *Evaluation of FORTA fibre-reinforced asphalt mixtures using advanced material characterization tests - Evergreen Drive, Tempe, Arizona*, Tempe, AZ, Arizona State University, 2008.

[29] Jaskuła, P., Stienss, M., Szydłowski, C., "Effect of polymer fibres reinforcement on selected properties of asphalt mixtures", *Procedia Engineering*, v. 172, pp. 441–448, Feb. 2017. doi: <http://dx.doi.org/10.1016/j.proeng.2017.02.026>
» <https://doi.org/10.1016/j.proeng.2017.02.026>

[30] EDGAR, R., *Ten year performance of asphalt additive test sections: lava butte fremont highway junction section*, Washington, D.C., Federal Highway Administration, 1998.

[31] Klinsky, L.M.G., Kaloush, K.E., Faria, V.C., *et al*, "Performance characteristics of fiber modified hot mix asphalt", *Construction & Building Materials*, v. 176, pp. 747–752, Jul. 2018. doi: <http://dx.doi.org/10.1016/j.conbuildmat.2018.04.221>

This site uses cookies to ensure you get a better browsing experience. Read our [Privacy Policy](#).

» <https://doi.org/10.1016/j.conbuildmat.2018.04.221>

- [32] BUREAU OF INDIAN STANDARDS, *IS 73:2013 Paving Bitumen – Specification*, New Delhi, Brazil India, Bureau of Indian Standards.
- [33] AMERICAN SOCIETY FOR TESTING AND MATERIALS, *ASTM D1559 Standard Test Method for Resistance to Plastic Flow of Bituminous Mixtures Using Marshall Apparatus*, New Jersey, West Conshohocken, Wiley, 2018.
- [34] Maherz, A., KARIM, M.R., KATMAN, H.Y., “Fatigue and deformation properties of glass fibre reinforced bituminous mixes”, *Journal of the Eastern Asia Society for Transportation Studies*, v. 6, pp. 997–1007, 2005.
- [35] Morava, N., “Investigation of usability of basalt fibres in hot mix asphalt concrete”, *Construction & Building Materials*, v. 47, pp. 175–180, 2013. doi <http://dx.doi.org/10.1016/j.conbuildmat.2013.04.048>
» <https://doi.org/10.1016/j.conbuildmat.2013.04.048>
- [36] Supriya, C.B., MANJUNATH, B.H., DINESH S.V., “Influence of the fiber on improving mechanical properties of bituminous mixes”, *International Research Journal of Engineering and Technology*, v. 2, n. 1, pp. 90–94, 2013.
- [37] Taherkhani, H., “Investigating the properties of asphalt concrete containing glass fibres and nanoclay”, *Civil Engineering Infrastructures Journal*, v. 49, n. 1, pp. 45–58, 2016.
- [38] EUROPEAN STANDARD, *EN 12697-26 Bituminous Mixtures - Test Methods for Hot Mix Asphalt -Part 26: Stiffness*, Brussels, Belgium, European Standard, 2012.
- [39] BRITISH STANDARD, *BS EN-12697-24 Bituminous Mixtures — Test Methods for Hot Mix Asphalt - Part 24: Resistance to Fatigue*, United Kingdom, British Standard, 2012.
- [40] Jahromi, S.G., Khodaii, A., “Carbon fiber reinforced asphalt concrete”, *Arabian Journal for Science and Engineering*, v. 33, pp. 355–364, 2008.
- [41] Ramesh, A., Venkat, R.V., Sandeep, R.G., *et al*, “Investigations on fracture response of warm mix asphalt mixtures with Nano glass fibres and partially replaced RAP material”, *Construction & Building Materials*, v. 317, pp. 126121, 2022. doi: <http://dx.doi.org/10.1016/j.conbuildmat.2021.126121>
» <https://doi.org/10.1016/j.conbuildmat.2021.126121>
- [42] AMERICAN SOCIETY FOR TESTING AND MATERIALS, *ASTM D 6927 Standard Test Method for Marshall Stability and Flow of Bituminous Mixtures*, New Jersey, West Conshohocken, Wiley, 2005.
- [43] AMERICAN SOCIETY FOR TESTING AND MATERIALS, *ASTM D3549 Standard Test Method for Thickness or Height of Compacted Bituminous Paving*, New Jersey, West Conshohocken, Wiley, 2003.

This site uses cookies to ensure you get a better browsing experience. Read our [Privacy Policy](#).

- [44] Maherz, A., Karim, M.R., “Fatigue characteristics of stone mastic asphalt mix reinforced with fibre glass”, *International Journal of Physical Sciences*, v. 5, n. 12, pp. 1840–1847, 2010.

[45] Bocci, E., Prospero, E., "Recycling of reclaimed fibers from end-of-life tires in hot mix asphalt", Brazil *Journal of Traffic and Transportation Engineering*, v. 7, n. 5, pp. 678–687, 2020. doi:
http://dx.doi.org/10.1016/j.jtte.2019.09.006
» https://doi.org/10.1016/j.jtte.2019.09.006

Matéria (Rio de Janeiro) ▾

Publication Dates

- » **Publication in this collection**
25 Aug 2023
- » **Date of issue**
2023

History

- » **Received**
02 Apr 2023
- » **Accepted**
17 May 2023



This is an Open Access article distributed under the terms of the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

**Laboratório de Hidrogênio, Coppe - Universidade Federal do Rio de Janeiro, em cooperação com
a Associação Brasileira do Hidrogênio, ABH2**

Av. Moniz Aragão, 207, 21941-594, Rio de Janeiro, RJ, Brasil, Tel: +55 (21) 3938-8791 - Rio de Janeiro -
RJ - Brazil

E-mail: revmateria@gmail.com

This site uses cookies to ensure you get a better browsing experience. Read our [Privacy Policy](#).

OK

SciELO - Scientific Electronic Library Online

Brazil

Rua Dr. Diogo de Faria, 1087 – 9º andar – Vila Clementino 04037-003 São Paulo/SP - Brasil

E-mail: scielo@scielo.org

Matéria (Rio de Janeiro) ▾



Read our Open Access Statement

This site uses cookies to ensure you get a better browsing experience. Read our [Privacy Policy](#).

OK